

TDS og instruction

Microdispers tix

Micro dispersion primer thixotropic

Item no. 443-0000xx PR no 2361134

UFI: 5JKA-UVKS-F203-41MP



Thixotropic micro dispersion primer- fastening primer for priming of absorbent substrates before painting and wallpapering.

More viscous than traditional fastening primer, not as prone to dripping and spattering, as the traditional types.

Areas of application

Basic treatment of plaster, plasterboard, concrete, mud, putty and lime. For both interior and exterior use.

Substrate

Substrate must be clean, dry, firm, free from staining and suitable for painting.

Clean and rinse whitewashed surfaces until rinsing water is clear and free from lime.

Staining substrates such as nicotine, stains, soot etc. must be cleaned, primed with micro dispersion primer, thereafter; an appropriate stain stopper.

Treatment

Stir/shake well before and during use.

Apply with paintbrush or paint roller.

Priming is only done once and the primer must be completely absorbed by the substrate.

Note:

If too much microdispersion is applied, creating a glossy layer when dry.

If primed substrate looks lacquered when dry, it has been excessively primed. If so, sand before painting, as excessive priming causes bad adhesion.

Apply appropriate paint within two weeks after priming with micro dispersion primer.

The mentioned information is based on laboratory experiments and practical testing at 20°C and 85% RH. If the temperature or humidity of the material, the substrate or the surroundings deviate from this, the product properties, drying and curing times are affected. A general responsibility for paint treatment cannot be given, due to the many caveats that may arise regarding the substrate, application method, etc. Where the consumption of a paint extend over more batches, these should be intermixed to avoid sheen and shade differences. It is the user's responsibility to always obtain new and revised product sheets. We reserve the right to make changes without notice. We reserve the right for printing errors. In case of inconsistency between language versions, the Danish version applies.

Type: Micro dispersion primer

Areas of application:

Absorbent, mineral substrate, interior and exterior use

Binder: Acrylic micro dispersion

Thinning: Dilute with water

Density: Approx. 1 kg/l ISO 2811

Viscosity (20°C): cP 200 ISO 2555

Consumption: 60-70 ml/m², depending on application method and substrate

Application: Paintbrush or paint roll

Drying time v. 20°C/60% RH: 4 hours

Application temperature:

Developed for use at 10°C-25°C

Min. +5°C - Max. 30°C

(substrate and surroundings)

Humidity:

Best at 60%-65% RH

Min. 40% max. 80% RH

Cleaning tools:

Water and soap

Storage:

Store at +5°C-+25°C, not in direct sunlight and inaccessible to children

Shelf life:

Min. 24 months from production date when stored correctly (Batch no. yymmdd)

Packaging: 2½ litre canister

Colours: Transparent, greenish

VOC value: <30 g/l

EU VOC limit value (2010):

Kat A/a: 30 g/l

CLP symbols: None

CLP signal word: None

MAL code: 00-1

Permeability: class EN 7783-2

Document date: 13-10-2022



Promal A/S • Joachim Wellers Vej 27 • DK-7500 Holstebro
+45 9610 5080 • info@promal.dk • www.promal.dk