

TDS og instruction

Facademaling gl. 2

Oil emulsion - facade paint

Item no. 480-XXXX04 PR no. 2361011

UFI: 76KA-TVU6-7203-GP9E



Facademaling glans 2 is a rich and permeable facade paint with anti-fouling agents.

Helps protect the substrate from weathering and resulting degradation.

Areas of application

Painting of dry, absorbant substrates such as plaster, concrete, lightweight concrete, tile, lime, sandstone and mineral slate.

Can be used on firmly seated lime and on cement based paint.

Substrate

Substrate must be clean, dry, firm and free from staining.

Staining substrates must be thoroughly cleaned, and primed with suitable primer.

Som substrates require special primer to ensure good adhesion.

Untreated mineral substrate that are still alkaline as well as strongly degraded substrate must be primed with microdispersion-primer.

Other mineral substrates should be primed with diluted facade paint.

Treatment

Stir extremely well before and during use.

Apply with paintbrush, paint roller or sprayer.

Expect application of minimum 2 coats of paint.

Note:

Facade paint gl. 2 is unsuitable for use on silicat- and silicone based paints.

Type: Acrylic/oil emulsion,
Wall- & facade paint

Areas of application: Facade walls

Binder: Oil & acrylic

Thinning: Dilute with water

Density: Approx. 1,3 kg/l ISO 2811

Viscosity (at 20°C): cP 3000

Gloss (at 60° angle): Approx. 2, flat

Consumption: 3-8 m²/l

Drying time at 23°C/50% RH: 4-6 hours

Next coat (at 20°C - 85% RH):

When dry, but min. 6 hours

Fully durable: After 7 days

Application temperature:

Developed for use at 10°C-25°C

Min. +5°C - Max. 30°C

(substrate and surroundings)

Humidity:

Best at 60%-65% RH

Min. 40% max. 80% RH

Cleaning tools:

Water and detergent

Storage:

Store at +5°C-+25°C, not in direct sunlight, and inaccessible to children

Shelf life:

Min. 24 months from date of production when stored correctly (Batchnr: ååmmdd)

Packaging: 10 litre bucket

Colour:

White, black and Base C for tinting

VOC-value: <30 g/l

EU VOC limit (2010):

Cat. A/a: 30 g/l

CLP symbols: None

CLP signal word: None

MAL-kode: 00-1

Washable: Class 1 En13300

Permeability: Class 1 jf. EN 7783-2

Adhesion: GT≤1 jf. EN 2409

Document date: 20-11-2022

The mentioned information is based on laboratory experiments and practical testing at 20°C and 85% RH. If the temperature or humidity of the material, the substrate or the surroundings deviate from this, the product properties, drying and curing times are affected. A general responsibility for paint treatment cannot be given, due to the many caveats that may arise regarding the substrate, application method, etc. Where the consumption of a paint extend over more batches, these should be intermixed to avoid sheen and shade differences. It is the user's responsibility to always obtain new and revised product sheets. We reserve the right to make changes without notice. We reserve the right for printing errors. In case of inconsistency between language versions, the Danish version applies.



Promal A/S • Joachim Wellers Vej 27 • DK-7500 Holstebro
+45 9610 5080 • info@promal.dk • www.promal.dk