

**001RS | HSS FULLY GROUND  
JOBBER LENGTH DRILL. REDUCED  
SHANK**



**HSS**

**STEAM  
TREATED**

**DIN  
338**

**3xd**


**h8**

**118°**

**N  
TYPE**

**001RS | BROCA HSS RECTIFICADA  
CILÍDRICA. SERIE CORTA. MANGO  
REDUCIDO.**

**001RS | PUNTA HSS CILINDRICA  
CORTA. TIPO N | GAMBO RIDOTTO.**



For steels and cast irons. Robustness, accuracy.

Para Aceros y fundiciones. Robustez, precisión.

Foratura di acciai <950 N/mm<sup>2</sup> e ghise. Robustezza e precisione.

**AB**

Steels for heat treatment 200-700N/mm<sup>2</sup>  
Aceros para tratamiento térmico 200-700 N/mm<sup>2</sup>  
Acciai per trattamento termico 200-700N/mm<sup>2</sup>

**C**

Heat Treatable Steels <950N/mm<sup>2</sup>  
Aceros aleados y tratados < 950N/mm<sup>2</sup>  
Acciai per trattamento termico <950N/mm<sup>2</sup>

**H**

Austenitic stainless steels  
Aceros inoxidables austeníticos  
Acciai inossidabili austenitici

**IJ**

Cast iron  
Fundiciones  
Ghisa

1140041	EAN	Ø	d2	L	I1	QTY	PCB
11400411300	3221910126735	13	10	151	101	1	1
11400411350	3221910126766	13.5	12	160	108	1	1
11400411400	3221910126780	14	12	160	108	1	1
11400411450	3221910126810	14.5	12	169	114	1	1
11400411500	3221910126834	15	12	169	114	1	1
11400411550	3221910126872	15.5	12	178	120	1	1
11400411600	3221910126896	16	12	178	120	1	1
11400411650	3221910126926	16.5	12	184	125	1	1
11400411700	3221910126940	17	12	184	125	1	1
11400411750	3221910126964	17.5	12	191	130	1	1
11400411800	3221910126971	18	12	191	130	1	1
11400411850	3221910126995	18.5	12	198	135	1	1
11400411900	3221910127008	19	12	198	135	1	1
11400411950	3221910127022	19.5	12	205	140	1	1
11400412000	3221910127046	20	12	205	140	1	1
11400412100	3221910127077	21	12	205	140	1	1
11400412200	3221910127091	22	12	210	150	1	1
11400412300	3221910127121	23	12	210	150	1	1
11400412400	3221910127145	24	12	220	160	1	1
11400412500	3221910127169	25	12	220	160	1	1



**Conditions de Coupe. Werkomstandigheden. Schnittbedingungen. Cutting conditions.**  
**Condiciones de corte. Condizioni d'impiego**

**Forets. Spiraalboren. Spiralbohrer. Drills. Brocas. Punte.**

Vc (M/min) f (mm/rt)	HSS to HSCo					CARBIDE																	
						Standard					Hight performance												
	Vc	f:	Ø2	Ø5	Ø10	Ø15	Vc	f:	Ø2	Ø5	Ø10	Ø15	Vc	f:	Ø2	Ø5	Ø10	Ø15					
<b>A</b>	Aciers non alliés / faiblement alliés Niet-of licht gelegeerd Staal Unligierte oder schwachlegierte unalloyed & low alloyed steels Aceros de construcción o aceros poco aleados Acciai non legati o poco legati <b>&lt;400N/mm²</b>					<b>32</b>	f:	0,06	0,12	0,3	0,4	<b>100</b>	f:	0,03	0,05	0,08	0,12	<b>140</b>	f:	0,07	0,13	0,25	0,4
<b>B</b>	Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico <b>&lt; 700 N/mm²</b>					<b>28</b>	f:	0,06	0,12	0,3	0,4	<b>100</b>	f:	0,03	0,04	0,07	0,1	<b>140</b>	f:	0,06	0,12	0,25	0,4
<b>C</b>	Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico <b>&lt; 950 N/mm²</b>					<b>20</b>	f:	0,03	0,07	0,18	0,24	<b>80</b>	f:	0,02	0,03	0,06	0,08	<b>120</b>	f:	0,06	0,12	0,25	0,4
<b>D</b>	Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico <b>&lt; 1200 N/mm²</b>					<b>16</b>	f:	0,04	0,09	0,18	0,28	<b>60</b>	f:	0,02	0,03	0,06	0,08	<b>100</b>	f:	0,06	0,12	0,25	0,4
<b>E</b>	Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico <b>&lt; 1400 N/mm²</b>					<b>NC</b>	f:	-	-	-	-	-	f:	-	-	-	-	-	f:	-	-	-	-
<b>F</b>	Aciers inoxydables, Ferritiques Roestvrij Ferrietaal Rostfreies Stähle, Ferritisch Stainless Steels, Ferritic Aceros inoxidables, Ferriticos Acciai inossidabili, Ferritici					<b>16</b>	f:	0,04	0,09	0,21	0,28	<b>60</b>	f:	0,01	0,05	0,08	0,1	<b>70</b>	f:	0,04	0,08	0,15	0,25
<b>G</b>	Aciers inoxydables, Martensitiques Roestvrij Martensietstaal Rostfreies Stähle, Martensitisch Stainless Steels, Martensitic Aceros inoxidables, Martensiticos Acciai inossidabili, Martensitici					<b>14</b>	f:	0,03	0,07	0,18	0,28	<b>60</b>	f:	0,01	0,05	0,08	0,1	<b>60</b>	f:	0,03	0,06	0,13	0,2
<b>H</b>	Aciers inoxydables, Austénitiques Roestvrij Austenietstaal Rostfreies Stähle, Austenitisch Stainless Steels, Austenitic Aceros inoxidables, Austeniticos Acciai inossidabili, Austenitici					<b>12</b>	f:	0,04	0,09	0,21	0,28	<b>40</b>	f:	0,01	0,05	0,08	0,1	<b>60</b>	f:	0,03	0,06	0,13	0,2
<b>I</b>	Fontes grises Graw gietijzer Grauguss Cast Iron Fundición gris Ghisa grigia					<b>30</b>	f:	0,06	0,12	0,3	0,4	<b>80</b>	f:	0,01	0,05	0,08	0,1	<b>100</b>	f:	0,08	0,16	0,24	0,3

**Conditions de Coupe. Werkomstandigheden. Schnittbedingungen. Cutting conditions.**  
**Condiciones de corte. Condizioni d'impiego**

**Forets. Spiraalboren. Spiralbohrer. Drills. Brocas. Punte.**

Vc (M/min) f (mm/tr)	HSS to HSCo					CARBIDE												
						Standard					High performance							
	Vc	f	Ø2	Ø5	Ø10	Ø15	Vc	f	Ø2	Ø5	Ø10	Ø15	Vc	f	Ø2	Ø5	Ø10	Ø15
<b>J</b> Fontes GS Gietijzer SG SG Guss SG Iron Fundición gris con grafito laminar Ghisa a Grafite Steroidale	<b>16</b>	f:	0,04	0,09	0,21	0,28	<b>50</b>	f:	0,01	0,05	0,08	0,1	<b>90</b>	f:	0,04	0,08	0,16	0,25
<b>K</b> Allages d'aluminium gras Zilvere aluminiumlegeringen Reinaluminium Aluminium Forgings Aleaciones de aluminio Laminato (Al)	<b>80</b>	f:	0,05	0,1	0,24	0,32	<b>150</b>	f:	0,03	0,08	0,13	0,16	<b>400</b>	f:	0,03	0,06	0,14	0,24
<b>L</b> Allages d'aluminium Aluminiumlegeringen Aluminium-legierungen Cast Aluminium Aleaciones de aluminio Stampate Al <b>Si &lt; 10%</b>	<b>60</b>	f:	0,04	0,09	0,21	0,28	<b>150</b>	f:	0,03	0,08	0,13	0,16	<b>350</b>	f:	0,02	0,05	0,12	0,2
<b>M</b> Allages d'aluminium Aluminiumlegeringen Aluminium-legierungen Cast Aluminium Aleaciones de aluminio Stampate Al <b>Si &gt; 10%</b>	<b>40</b>	f:	0,04	0,09	0,21	0,28	<b>80</b>	f:	0,01	0,06	0,09	0,12	<b>300</b>	f:	0,02	0,05	0,12	0,2
<b>N</b> Laiton Messing Messing Brass Laton Ottone	<b>60</b>	f:	0,05	0,1	0,24	0,32	<b>100</b>	f:	0,03	0,06	0,1	0,15	<b>nc</b>	f:	nc	nc	nc	nc
<b>O</b> Bronze Brons Bronze Bronze Bronce Bronzo	<b>60</b>	f:	0,04	0,09	0,21	0,28	<b>100</b>	f:	0,02	0,05	0,09	0,12	<b>nc</b>	f:	nc	nc	nc	nc
<b>ARCO/ AR Ni</b> Aciers réfractaires base Co Ni Hittebestendige legeringen op basis van Co Ni Hitzebeständige Legierungen, Co Ni base Special Alloys based Co Ni Aleaciones refractarias, base Co Ni Leghe refrattarie, Co Ni base	<b>10</b>	f:	0,02	0,04	0,1	0,17	<b>20</b>	f:	0,01	0,03	0,05	0,08	<b>30</b>	f:	0,02	0,05	0,1	0,16
<b>Ti</b> Allages de Titane Titaanlegeringen Titanlegeringen Titan alloys Aleaciones de titanio Titanio	<b>10</b>	f:	0,02	0,04	0,1	0,17	<b>20</b>	f:	0,01	0,03	0,05	0,08	<b>30</b>	f:	0,02	0,05	0,1	0,16