



HSSE DIN MACHINE TAP GUN.

MACHO DE MÁQUINA HSSE DIN GUN.

MASCHIO A MACCHINA HSS-E DIN GUN.



Steel tapping < 700 N/mm². Robustness, accuracy.

Roscado de aceros < 700 N/mm². Robustez, precisión.

Filettatura degli acciai <700 N/mm². Robustezza e precisione.



Heat Treatable Steels <400N/mm²
Aceros aleados y tratados < 400N/mm²
Acciai per trattamento termico <400N/mm²



Heat Treatable Steels <700N/mm²
Aceros aleados y tratados < 700N/mm²
Acciai per trattamento termico <700N/mm²



Aluminium alloys
Aleaciones de aluminio
Leghe di alluminio

9623021	EAN	Ø	P	L	I	d2	DIN	QTY	PCB
962302100140200	8420609342882	C1/4	20	80	16	4.5	376	1	1
962302100516180	8420609342943	C5/16	18	90	18	6	376	1	1
962302100380160	8420609342929	C3/8	16	90	18	7	376	1	1
962302100716140	8420609342981	C7/16	14	100	22	8	376	1	1
962302100120130	8420609342868	C1/2	13	110	25	9	376	1	1
962302100580110	8420609342967	C5/8	11	110	28	12	376	1	1
962302100340100	8420609342905	C3/4	10	125	32	14	376	1	1
962302100780090	8420609343001	C7/8	9	140	32	18	376	1	1
962302110000080	8420609343063	C1"	8	160	36	20	376	1	1



9623021	EAN	Ø	P	L	I	d2	DIN	QTY	PCB
962302100380240	8420609342936	F3/8	24	100	18	7	376	1	1
962302100716200	8420609342998	F7/16	20	100	22	8	376	1	1
962302100120200	8420609342875	F1/2	20	110	25	9	376	1	1
962302100580180	8420609342974	F5/8	18	110	25	12	376	1	1
962302100340160	8420609342912	F3/4	16	125	32	14	376	1	1
962302100780140	8420609343018	F7/8	14	125	32	18	376	1	1
962302110000120	8420609343070	F1"	12	140	32	20	376	1	1



Conditions de Coupe. Werkomstandigheden. Schnittbedingungen. Cutting conditions. Condiciones de corte. Condizioni d'impiego.

Tarauds. Draadsnijtappen. Gewindebohrer. Taps. Machos. Maschio.

Vc (M/min) Revêtement / coating = Vc + 20 => 50%



A	<p>Aciers non alliés / faiblement alliés Niet-of licht gelegeerd Staal Unligierte oder schwachlegierte unalloyed & low alloyed steels Aceros de construcción o aceros poco aleados Acciai non legati o poco legati <400N/mm²</p>	25-30	18-20	18-20	15-18	15-18
B	<p>Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico < 700 N/mm²</p>	20-30	15-18	15-18	15-18	20-25
C	<p>Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico < 950 N/mm²</p>		6-8	6-8	6-8	5-8
D	<p>Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico < 1200 N/mm²</p>		4-6	4-6	4-6	2-5
E	<p>Acier pour traitement thermique Staal voor thermische behandeling Vergütungsstähle Heat Treatable Steels Aceros aleados y tratados Acciai per trattamento termico < 1400 N/mm²</p>			3-5		3-5
F	<p>Aciers inoxydables, ferritiques Roestvrij ferrietaal Rostfreies Stähle, ferritisch Stainless Steels, Ferritic Aceros inoxidables, ferríticos Acciai inossidabili, ferritici</p>	10-20		6-8		6-8
G	<p>Aciers inoxydables, Martensitiques Roestvrij Martensietstaal Rostfreies Stähle, Martensitisch Stainless Steels, Martensitic Aceros inoxidables, Martensíticos Acciai inossidabili, Martensitici</p>			4-6		4-6
H	<p>Aciers inoxydables, Austénitiques Roestvrij Austenietstaal Rostfreies Stähle, Austenitisch Stainless Steels, Austenitic Aceros inoxidables, Austeníticos Acciai inossidabili, Austenitici</p>			5-7		5-7
I	<p>Fontes grises Graw gietijzer Grauguss Cast Iron Fundición gris Ghisa grigia</p>		15-20			

Conditions de Coupe. Werkomstandigheden. Schnittbedingungen. Cutting conditions. Condiciones de corte. Condizioni d'impiego.

Tarauds. Draadsnijtappen. Gewindebohrer. Taps. Machos. Maschio.

Vc (M/min) Revêtement / coating = Vc + 20 => 50%



J	Fontes GS Gietijzer SG SG Guss SG Iron Fundición gris con grafito laminar Ghisa a Grafite Sferoidale		10-15			
K	Alliages d'aluminium gras Zuivere aluminiumlegeringen Rein aluminium Aluminium Forgings Aleaciones de aluminio Laminato (Al)	30-40		15-25		15-25
L	Alliages d'aluminium Aluminiumlegeringen Aluminium-legierungen Cast Aluminium Aleaciones de aluminio Stampate Al Si < 10%	12-20		12-18		12-18
M	Alliages d'aluminium Aluminiumlegeringen Aluminium-legierungen Cast Aluminium Aleaciones de aluminio Stampate Al Si > 10%	12-20		12-18		12-18
N	I aiton Messing Messing Brass Laton Ottonie	25-30	18-20	18-20	15-18	15-18
O	Bronze Brons Bronze Bronze Bronze Bronzo		5-10	5-10	5-10	4-8
ARCO/ AR Ni	Aciers réfractaires base Co Ni Hittebestendige legeringen op basis van Co Ni Hitzebeständige Legierungen, Co Ni base Special Alloys based Co Ni Aleaciones refractarias, base Co Ni Leghe refrattarie, Co Ni base		2-4	2-4	2-4	2-4
Ti	Alliages de Titane Titaanlegeringen Titaniegeringen Titan alloys Aleaciones de titanio Titanio			3-5		3-5