



Snelcore BV
Bruningweg 1
6827 BM Arnhem
P.O. Box 2068
6802 CB Arnhem
The Netherlands
Tel.: +31 26 750 23 40
Fax: +31 26 750 23 41

F. van Lanschot Bank Nijmegen
Account nr.: 22.54.34.792
Swift code : FVLBNL22
IBAN nr.: NL17FVLB0225434792
Website: www.snelcore.com
E-mail: info@snelcore.com
VAT nr.: NL 007328692B01
Chamber of Commerce 09055836

APET PT 200

Product

Clear APET Film

Film Composition

Co-Extruded APET : APET / Recycled / APET
or APET / Recycled + APET / APET

Applications

Packaging for Food, Fruit / Vegetables, Electronical / Technical parts,
Blisters.

Properties

Density	1.33 g / cm ³	DIN 53479
E - Modulus	2200 - 2400 N/mm ²	DIN 53457
Max. Temp. Resistance	70 °C	DIN 53460
Min. Temp. Resistance	20 °C min	DIN 53460
Sterilisation	Gamma + ETO	
Heat Sealing	Ultra Sonic	
Glueing	Possible with hotmelts	
Printing	Possible.	

Specifications

Thicknesses	from 0,18 up to 1,3 mm.
Widths	from 300- up to 1400 mm.
Cores	76- and 150 mm.
Rollsizes	Up to 900 mm.

**To improve denesting, various levels / qualities of Anti-blocking are available.
Colours are available on request (White, Brown + Black STANDARD).
Industrial scrap is fully recycable.**

**Resins and additives used, meet all international requirements (FDA + EU)
with regards to food contact.**

Absence of Heavy Metals (EU 94 / 62 EC).

This datasheet is believed to be reliable and given in good faith. All information is based on Snelcore's general knowledge and experience, but we can not be held liable in respect of application, processing or use of the information or product.

aug-08