

Afdækningsfolie af Poyethylene

| | |
|----------------------------------|---|
| Film Thickness acc to GKV | 0.03 / 0.05 / 0.07 / 0.10 / 0.12 / 0.15 / 0.20 / 0.30 / 0.40 mm * |
| Film Width acc to GKV | 1.000 – 12.000 mm * |
| Colour | Black * |

* Not all of the wide and thick communications are available / Other dimensions on request

Properties (typical values)

| | Value | Unit | Method |
|---------------------|-------|-------------------|------------------|
| Tensile Strength MD | ≥ 15 | N/mm ² | DIN EN ISO 527-3 |
| Tensile Strength CD | ≥ 14 | N/mm ² | DIN EN ISO 527-3 |
| Elongation MD | ≥ 250 | % | DIN EN ISO 527-3 |
| Elongation CD | ≥ 250 | % | DIN EN ISO 527-3 |
| Dart Drop | ≥ 1 | g/μm | ASTM D 1709 |

Resistance to bitumen

According to the literature, LDPE is resistant to bitumen at normal ambient temperatures. So we assume that our films are also resistant. The product was not tested. The processor is responsible to determine the suitability for a particular purpose by their own tests and trials.

Conditions of storage

This film is not protected against UV-radiation. The films should be protected against UV radiation, moisture and other weather influences. The film should be processed within one year after delivery. The temperature for processing should be between 15-30 ° C. Mechanical damages of the film are to be avoided.