

PaperlinX  
 CC&CO A/S  
 Bastrupgaardvej 8 - 10  
 DK 7500 Holstebro

Product data sheet

topsheets



Article description:  
 Dimensions:  
 Product data sheet

PE-topsheets  
 800 / 1350 / 0,03 mm  
 Nr. B / 407 / 2014

1.0	Product description		Production tolerances	DIN standard
1.1	article description:	PE-topsheets		
1.2	Dimensions	800 / 1350	+/- 6 mm	GKV
1.3	Thickness	30 µm	+ / - 13 %	GKV
	Area density	27,60 g/m <sup>2</sup>	+ / - 7 %	GKV
1.4	Coloring	transparent		
1.5	Features	antistatic		
1.6	Packing	on rolls with 200 pieces, on card-board cores with inner diameter 76 mm, on Euro pallets		
1.7	Printing	without		
2.0	Specifications		Production tolerances	DIN standard
2.1	Basic commodity	Polyolefins in accordance with DIN EN ISO 1043		
2.2	Density	0.92 g/cm <sup>3</sup>	+/- 10 %	ISO 1183-1
2.3	Melt flow index	2,0 g/10 min	+/- 10 %	ISO 1133
2.4	Tensile Strain at Break MD	> 350 %	10 %	ISO 527-3
	Tensile Strain at Break TD	> 350 %	10 %	
2.5	Tensile Strength MD	> 20 N/mm <sup>2</sup>	10 %	ISO 527-3
	Tensile Strength TD	> 18 N/mm <sup>2</sup>	10 %	
2.6	Sliding Coefficient			ISO 8295
	Foil – Foil	0,1	+/- 0.1	
	Foil – Metal	0,15	+/- 0.1	
2.7	Vicat Softening Temperature	93° C		ISO 306
2.8	Melting temperature	180 – 205 ° C		DSC
3.0	Other			
3.1	Production methode	Blown Film - Coextrusion		
3.2	Weldingability	Mind. 70 % of the film strength, without residues		