


CODE : FLM1598 DATE: 04/11/2022

PETCX GLOSS WHITE 85 / AP901 / WG62

PRODUCT DESCRIPTION / BENEFITS Face: Gloss white cavitated polyethylene.

Adhesive: Acrylic permanent adhesive featuring high clarity and cohesion with strong adhesion to apolar substrates (like PE and PP).

Liner: White supercalendered glassine paper. There may be slight variations in tone.



TYPICAL USE

Health & Personal Care

PRINTING & CONVERTING

Suited to provide top printing quality in all usual conventional processes (flexo, screen, offset, gravure, hot-stamping, TTR) standard and low migration UV inks. Suitable for UV Inkjet printing. Testing for suitability between media, printers and inks is always recommended prior to use.

PRODUCT RECOMMENDATIONS

Flexible labels for the cosmetics, personal and home care industries.

SHELF LIFE

2 years, under storage conditions as defined by FINAT section 2.5 (20-25°C, 40-50% RH). Prolonged storage at higher temperatures and/or humidity levels will shorten the shelf life of the product.



CODE : FLM1598 DATE: 04/11/2022

PETCX GLOSS WHITE 85 / AP901 / WG62

PHYSICAL PROPERTIES / TYPICAL VALUES

FACE MATERIAL			
PE TCX GLOSS WHITE	85		
Grammage	79 Gr/m2	ISO 536	
Thickness	80 µm	ISO 534-80	
Finishing	Gloss White		

ADHESIVE			
AP901			
Tack (N) Glass	8 N/mm	FTM9	
Min Labelling temperature	-5 °C		
Usage Temperature	-40/+80 °C		
Peel Value	7 (N/25mm) 24h	FTM2	

LINER				
WG62				
Grammage	58 Gr/m2	ISO 536		
Thickness	51 µm	ISO 534-80		

QUALITY CERTIFICATIONS • Suitable for direct food contact with dry, moist and such kind of fatty foodstuffs with a correction factor of at least 3. More information on request.

DISCLAIMER

Information on physico-chemical characteristics and values in this document are based upon tests we believe to be reliable and do not constitute a warranty. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change. All Fedrigoni products are sold subject to terms and conditions of sale. For more information, contact your Fedrigoni sales representative. In case of any ambiguities or differences between the English and foreign versions of this document, the English version shall be prevailing and leading.