

# Data Sheet

## Testliner

Specifikation	Test method	Value				Variation	Unit
Basis weight	ISO 536	<b>120</b>	<b>150</b>	<b>180</b>	<b>220</b>	± 3 %	g/m <sup>2</sup>
Burst	ISO 2759	290	365	395	485		kPa
SCT CD	ISO 9895	1,8	2,25	2,55	3,25		kN/m
Cobb	ISO 535	50	50	50	50		g/m <sup>2</sup>
Moisture	ISO 287	7,5	7,5	7,5	7,5	± 3 %	%

## Grey Board

Specifikation	Standard	Value			Variation	Unit
Basis weight	ISO 536	<b>250</b>	<b>300</b>	<b>400</b>	± 5 %	g/m <sup>2</sup>
Stiffness	DIN 53121	9,0	16,1	38,2	± 15 %	MNM
Flexion	DIN 53121	4,7	8,5	20,0	± 15 %	MNM
Moisture	ISO 287	7	7	7	± 3 %	%
Burst	ISO 2759	340	390	490		kPa

## Antim65 / Antim Light®

Specifikation	Standard	Value						Variation	Unit
Basis weight	ISO 536	<b>100 Light</b>	<b>110</b>	<b>150 Light</b>	<b>150</b>	<b>220</b>	<b>300</b>	± 8 %	g/m <sup>2</sup>
Breaking lenght MD	ISO 1924-2	5,18	5,18	8,5	8,5	10,8	11,5		kN/m
Strain MD	ISO 1924-2	1,2	1,2	1,8	1,8	2,2	0,9		%
Breaking lenght CD	ISO 1924-2	2,32	2,32	2,5	2,5	3,0	3,3		kN/m
Strain CD	ISO 1924-2	2,7	2,7	3,3	3,3	4,4	4,6		%
Gripping Qualities	NFQ 03 – 083	≥ 40	≥ 50	≥ 40	≥ 50	≥ 50	45		°
Burst	ISO 2759	314	314	352	352	441	465		kPa



**ENVIRONMENTALLY FRIENDLY**  
100% RECYCLABLE

As we use recycled paper / cardboard, there may be colour differences.

**Coating:** Water-based emulsion

Approved as non-slip paper in the field of food packaging, certificated by ISEGA Germany.



PAL-Cut A/5 | Borbjerg | DK-7500 Holstebro  
Tel. +45 9613 3110 | info@palcut.com | www.palcut.com