



Twine & Rope A/S  
 Hvidkærvej 52  
 DK-5250 Odense SV

Tel +45 65 93 03 57  
 Fax +45 65 93 27 57  
 post@twine-rope.dk  
 www.twine-rope.dk

**TWINE  
&  
ROPE**  
 SINCE 1892

### Components of each quality (Phr)

	<b>Crepe A 100% rubber</b>	<b>Crepe B 84% rubber</b>	<b>Compound A 70% rubber</b>	<b>Compound B 60% rubber</b>
Rubber Bands	100	100	100	100
Filler	-	20	60	80
Sulpher	1,50	1,50	1,50	1,50
Antioxidant	1	1	1	1
Rubber oil	5	5	7	7
Accelerator	0.8-1.0	0,8-1.0	0.8-1.0	0.8-1.0
ZnO	-	3	5	5
Zn CO3	3	-	-	-

Dokumentation oplyst fra vor producent på hvilke råstoffer, der findes i forskellige kvaliteter af gummibånd

