

TROJAN° DATA SHEET MOTIVE OVERDRIVE™ AES 31

MODEL OverDrive™ AES 31

VOLTAGE 12

CAPACITY 104Ah @ 20Hr
MATERIAL Polypropylene

BATTERY VRLA AGM / Non-Spillable / Maintenance-Free

COLOR Maroon

WATERING No Watering Required





12 VOLT

PHYSICAL SPECIFICATIONS

BCI	MODEL NAME	TERMINAL TYPE	DIMENSIONS © INCHES (mm)			WEIGHT LBS. (kg)	HANDLES	INSTALLATION ORIENTATION
04	OVERDRIVE™		LENGTH	WIDTH	HEIGHT F	(- ()	<u> </u>	Horizontal
31 AES 31	AFO Od SI	12.80 (325)	6.81 (173)	9.43 (240)	69 (31)	Plastic Handle	and Vertical	

ELECTRICAL SPECIFICATIONS

VOLTAGE	AGE CRANKING PERFORMANCE		CAPACITY A MINUTES	CAPACITY ^B AMP-HOURS (Ah)		ENERGY (kWh)	INTERNAL RESISTANCE (mΩ)	SHORT CIRCUIT CURRENT (amps)		
12	C.C.A. ^D @0°F	C.A. ^E @32°F	@ 25 Amps	5-Hr	10-Hr	20-Hr	100-Hr	100-Hr	4.00	2555
12	540	648	178	83	92	104	115	1.38	4.80	

CHARGING INSTRUCTIONS

CHARGER VOLTAGE SETTINGS (AT 77°F/25°C)					
SYSTEM VOLTAGE	12V 24V		36V	48V	
Maximum Charge Current (A)	50% of C ₂₀				
Absorption Voltage (2.40 V/cell)	14.40	28.80	43.20	57.60	
Float Voltage (2.25 V/cell)	13.50	27.00	40.50	54.00	

Do not install or charge batteries in a sealed or non-ventilated compartment. Constant under or overcharging will damage the battery and shorten its life as with any battery.

CHARGING TEMPERATURE COMPENSATION

ADD	SUBTRACT
0.005 volt per cell for every 1°C below 25°C 0.0028 volt per cell for every 1°F below 77°F	0.005 volt per cell for every 1°C above 25°C 0.0028 volt per cell for every 1°F above 77°F

OPERATIONAL DATA

OPERATING TEMPERATURE	SELF DISCHARGE
-40°F to 140°F (-40°C to $+60$ °C). At temperatures below 32°F (0°C) maintain a state of charge greater than 60%.	Less than 3% per month depending on storage temperature conditions

RECYCLE RESPONSIBLY







Din forhandler




GACELL A/S - Sletten 17 - DK 7500 Holstebro - 961 02 961


STATE OF CHARGE MEASURE OF OPEN-CIRCUIT VOLTAGE

PERCENTAGE CHARGE	CELL	12 VOLT
100	2.14	12.84
75	2.09	12.54
50	2.04	12.24
25	1.99	11.94
0	1.94	11.64


TROJAN OVERDRIVE™ AES 31 PERFORMANCE




PERCENT CAPACITY VS. TEMPERATURE



BATTERY DIMENSIONS (shown with ST)



SELF DISCHARGE VS. TIME



TERMINAL TYPE

11	ST	STUD
Thursday, and the same of the		Battery Height with Terminal in Inches (mm) 9.43 (240) Torque Values in-lb (Nm) 120 - 180 (14 – 20) Stud Size 3/8" – 16

- A. The number of minutes a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 V/cell. Capacities are The national of minutes a sate of year deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.

 The amount of amp-hours (Ah) a battery can deliver when discharged at a constant rate at 80°F (27°C) and maintain a voltage above 1.75 Vicell. Capacities are based on peak performance.
- C. Dimensions may vary depending on type of handle or terminal. Batteries should be mounted with 0.5 inches (12.7 mm) spacing imminum.

 D. C.C.A. (Cold Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 0°F (-18°C) at a voltage above 1.2 V/cell.
- E. C.A. (Cranking Amps) the discharge load in amperes which a new, fully charged battery can maintain for 30 seconds at 32°F (0°C) at a voltage above 1.2
- CAL Clothaning Analysis are deschaled before an amperes which a reversible place of the control and a second at 32 Voicel. This is sometimes referred to as marine cranting amps @ 32°F or M.C.A. @ 32°F. Height taken from bottom of the battery to the highest point on the battery. Heights may vary depending on type of terminal. Terminal images are representative only.
- Batteries in storage should be charged when they decline to 75% State of Charge (SOC).
- Weight may vary.















Designed in compliance with applicable BCI, DIN, BS and IEC standards. Tested in compliance to BCI and IEC standards.

